

ProRox® SL 960

ProRox SL 960 is a strong and rigid stone wool slab and is especially suitable for the thermal and acoustic insulation of constructions up to intermediate temperatures.



Product properties

Properties	Performance										Standard
Thermal Conductivity	T_m (°C)	50	100	150	200	250	300	350	400	500	EN 12667
	λ (W/mK)	0.039	0.045	0.052	0.060	0.071	0.081	0.094	0.107	0.140	
Nominal Density	100 kg/m ³ (6.2 lb/ft ³)										EN 1602
Maximum Service Temperature	500°C (932°F)										EN 14706
Reaction to Fire	EuroClass A1										EN 13501-1
Water Leachable Chloride Content	Chloride content < 10 ppm (AS - Quality)										EN 13468
Water Absorption	< 1 kg/m ²										EN 1609
Water vapour diffusion resistance	$\mu = 1$										EN 14303
Airflow Resistivity	> 60 kPa.s/m ²										EN 29053

Note: All information and data for technical parameters are based on laboratory testing.

Compliance

- ProRox SL 960 slabs fully comply with the requirements as set by internationally recognized standards like EN14303, CINI 2.2.01

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.



ROXUL ROCKWOOL Technical Insulation India Pvt Ltd
 Wing B-2, 2nd Floor, Unit No. 206,
 Boomerang, Near Chandivali Film
 Studio, Chandivali Farm Road,
 Andheri (E), Mumbai – 400 072,
 Maharashtra, India
 T (+91) 022 6715 7700
 F (+91) 022 6715 7710

ROXUL-ROCKWOOL Insulation India Pvt Ltd
 Plot - Z/4, Dahej SEZ, Dahej,
 District Bharuch – 392 130,
 Gujarat, India
 T (+91) 2641 264400
 F (+91) 2641 256292

Toll Free 18002669861