

# ProRox® WM 960

ProRox WM 960 is a lightly bonded heavy stone wool mat stitched on galvanised wired mesh with galvanised wire. The wired mat is especially suitable for industrial installations such as high-pressure steam pipes, reactors, furnaces, etc. where high demands are made on the temperature resistance of the insulation.



## Product properties in accordance with IS 8183

Properties <sup>1</sup>	Performance							Standard
	$T_m$ (°C)	50	100	150	200	250	300	
Thermal conductivity <sup>2</sup> at mean temperature	$\lambda$ (W/mK)	0.040	0.048	0.057	0.068	0.079	0.093	IS 3346
Nominal density		100 kg/m <sup>3</sup>						IS 3144
Max service temperature		650°C						ASTM C411 / C447
Heat resistance		No visible deterioration of fibrous structure. No evidence of self heating. No fusion of fibres at 550°C						IS 3144
Incombustibility		< 5 wt%						IS 3144
Reaction to fire		EuroClass A1 Surface burning characteristic; Flame spread = Passed, Smoke development = Passed						EN 13501-1 ASTM E84
pH		7-10						IS 3144
Sulphur content		< 0.3 vol%						IS 3144
Chloride content		Less than 10 ppm Conforms to the stainless steel corrosion specification as per ASTM C795						IS 3144 ASTM C692 / C871
Moisture absorption		Less than 1 wt%						IS 3144
Shot content		>250µm < 8 wt% >500µm < 3 wt%						IS 3144

- All information and data for technical parameters in this data sheet are based on laboratory testing
- Nominal values.

### Compliance

- ProRox WM 960 Wired Mat fully comply with the requirements as set by IS 8183 and other internationally recognized standards.
- Above product properties reflect only to IS standards. Compliance and Performance according to ASTM can be found on our website. Please contact our sales representatives for an extended list of approvals & certifications.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.



**ROXUL ROCKWOOL Technical Insulation India Pvt Ltd**  
Wing B-2, 2nd Floor, Unit No. 206,  
Boomerang, Near Chandivali Film  
Studio, Chandivali Farm Road,  
Andheri (E), Mumbai – 400 072,  
Maharashtra, India  
T (+91) 022 6715 7700  
F (+91) 022 6715 7710

**ROXUL-ROCKWOOL Insulation India Pvt Ltd**  
Plot - Z/4, Dahej SEZ, Dahej,  
District Bharuch – 392 130,  
Gujarat, India  
T (+91) 2641 264400  
F (+91) 2641 256292

**Toll Free 18002669861**

**ROCKWOOL Technical Insulation**  
www.rockwoolasia.com

PRODUCT DATA SHEET  
200 344IN-12/18\_V3 (EN)  
PROROX INDUSTRIAL INSULATION