

SeaRox® SL 320

SeaRox SL 320 is a semi-rigid slab of stone wool. Excellent properties for easy handling and installation.

Application

SeaRox SL 320 is primarily used for sound insulation. Perfect in combination as comfort insulation with noise reduction.



Product properties

Properties	Performance		Norm
Thermal conductivity	T (°C)	10	EN 12667
	λ (W/mK)	0,035	
Nominal density	60 kg/m ³		EN 1602 / IMO
Compressive strength	-		EN 826
Fire classification	Non-combustible Low flame-Spread Properties		Acc. IMO FTP code
Water absorption (short term)	< 1 kg/m ²		EN 1609
Max. Application Temperature	Wool: 250°C		-
Sound absorption directly mounted	$\alpha_w = 0,85$ Thickness: 50 mm		ISO 354 (approximated) Evaluated after ISO 11 654
Facings	-		IMO A.653(16) (low flame - spread)

Dimensions

SeaRox SL 320

Thickness (mm): 50 mm Length (mm): 1000 mm Width (mm): 600 mm
 Thickness (mm): 75 mm Length (mm): 1000 mm Width (mm): 600 mm

Local variations in standard dimensions might occur.



0575

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.