

# ProRox® SL 950

ProRox SL 950 is a strong and rigid stone wool slab and is especially developed for the thermal and acoustic insulation of high temperature columns and vessels.



## Product properties

Properties	Performance												Norms
Thermal conductivity	T (°C)	50	100	150	200	250	300	350	400	500	600	640	EN 12667
	$\lambda$ (W/mK)	0,039	0,045	0,053	0,062	0,073	0,084	0,097	0,112	0,144	0,185	0,203	ASTM C177
Maximum Service Temperature	640°C (1184°F)												EN 14706
	750°C (1382°F)												ASTM C411
Reaction to fire	Euroclass A1												EN 13501-1
	Surface burning characteristics; Flame spread=passed, Smoke development=Passed												ASTM E84 (UL 723)
Nominal density	80 kg/m <sup>3</sup> (5,0 lb/ft <sup>3</sup> )												EN 1602
Corrosion resistance	Conforms to the stainless steel corrosion specification as per ASTM test methods C 692 and C 871												ASTM C795
	Trace quantity of water leachable chloride ions: $\leq$ 10 ppm												EN 13468
Water Absorption	$<$ 1 kg/m <sup>2</sup>												EN 1609
	Water vapour absorption (Vapor sorption) $\pm$ 0,02%vol												ASTM C1104/C1104M
Water vapour diffusion resistance	$\mu = 1$												EN 14303
Designation code	MW EN 14303-T4(T3 if t<60)-ST(+)/640-WS1-CL10												EN 14303

## Compliance

ProRox SL 950 Slabs fully comply with the requirements as set by internationally recognized standards like EN14303, CINI 2.2.01 and ASTM C612 Type IA, IB, II, III, IVA and IVB.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.