

TECHNICAL INSULATION

ProRox® WM 950

ProRox WM 950 is a lightly bonded stone wool mat stitched on galvanised wire mesh using galvanised wire. The wired mat is suitable for thermal and acoustic insulation of industrial applications reaching high temperatures, such as industrial pipe work, boiler walls, furnaces and smoke ducts.



Product properties in accordance with ASTM C592

Properties ¹	Performance							Norms
Thermal conductivity ² at mean temperature	Tຼ (°C) λ (W/mK)	50 0.038	100 0.046	150 0.053	200 0.062	250 0.071	300 0.080	ASTM C177
Nominal density	80 kg/m³							ASTM C167
Maximum use temperature	650°C							ASTM C411 / C447
Linear shrinkage	Less than 2% (at max service temperature)							ASTM C356
Reaction to fire	EuroClass A1 Surface burning characteristic; Flame spread = Passed, Smoke development = Passed							EN 13501-1 ASTM E84
Chloride content	Less than 10 ppm Conforms to the stainless steel corrosion specification as per ASTM C795							ASTM C871 ASTM C692 / C871
Moisture absorption	Less than 1% weight							ASTM C1104 / C1104N
Water absorption	Less than 1 kg/m²							EN 1609

- 1. All information and data for technical parameters in this data sheet are based on laboratory testing
- 2. Nominal values.

Compliance

- ProRox WM 950 Wired Mat comply with the requirements as set by internationally recognized standards like CINI 2.2.02 and ASTM C592 Type I, II and III
- Above product properties reflect only to ASTM standards. Compliance and Performance according to Indian Standards (IS) can be found on our website. Please contact our sales representatives for an extended list of approvals & certifications.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.



ROXUL ROCKWOOL Technical Insulation India Private Limited

Wing B-2, 2nd Floor, Unit No. 205, Boomerang, Near Chandivali Film Studio, Chandivali Farm Road, Andheri (E), Mumbai – 400 072, Maharashtra, India T (+91) 022 6715 7700 F (+91) 022 6715 7710 ROXUL-ROCKWOOL Insulation India Private Limited Plot - Z/4, Dahej SEZ, Dahej, District Bharuch – 392 130, Gujarat, India T (+91) 2641 264400

Toll Free 18002669861

ROCKWOOL Technical Insulation

www.rockwoolasia.com

PRODUCT DATA SHEET 200 332IN-07/20_V3 (EN) PROROX INDUSTRIAL INSULATION