



ProRox[®] LF 970





Product properties

Properties	Performance							Standard
Thermal Conductivity	T _m (°C)	50	100	150	200	250	300	EN 12667
	λ (W/mK)	0.040	0.049	0.057	0.067	0.075	0.091	
Maximum Service Temperature	680°C (1256°F)							EN 14706 ASTM C411
Reaction to Fire	Euroclass A1 Surface burning characteristics; Flame spread=passed, Smoke development=Passed							EN 13501-1 ASTM E84 (UL 723)
Water Absorption	$<$ 1 kg/m² $$$ Water vapour absorption (Vapor sorption) \pm 0,02%vol							EN 1609 ASTM C1104/C1104M
Water Leachable Chloride Content (AS Quality)	Chloride content < 10 ppm Conforms to the stainless steel corrosion specification as per ASTM test methods C692 and C871 < 10 mg/kg (ph-value neutral to slightly alkaline)							EN 13468 ASTM C795 ASTM C871
Water Vapour Diffusion Resistance	μ = 1							EN 12086

Note: All information and data for technical parameters are based on laboratory testing.

Compliance

ProRox LF 970 complies with the requirement as set by CINI 2.2.04.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL Malaysia Sdn Bhd

Lot 4, Solok Waja 1 Bukit Raja Industrial Estate 41050 Klang, Selangor, Malaysia T (+60) 3 3341 3444 F (+60) 3 3342 7290

ROCKWOOL Malaysia Sdn Bhd

175 A&B Kawasan Perindustrian Ayer Keroh, Jalan Lingkungan Usaha, 75450 Melaka Malaysia T (+60) 6 233 2010 F (+60) 6 233 2012

ROCKWOOL (Thailand) Limited

WHA Eastern Industrial Estate (Map Ta Phut)
No.1 Soi G2, Pakornsongkrohraj Road
Huaypong, Muang
Rayong 21150 Thailand
T (+66) 3868 5110
F (+66) 3868 4938